

PVC-U DWV

D00222588

DN225 X 45D DWV PVC-U Bend FF SWJ



Application

Used for non-pressure sewer, drain, waste and vent in above ground and below ground applications.

Features

- Australian made
- BEP PVC - manufactured from Best Environmental Practice
- Corrosion resistant
- Electrically nonconductive

Technical Data

Product Properties

Material	PVC
Colour	Light grey
Joint type	Solvent Weld Joint
Unprotected UV exposure	24 months

Product Dimensions²

Nominal size (mm)	225mm
Angle (degrees)	88
Mean Pipe ID	104mm
Wall thickness	3mm

Material Properties

Specific gravity	1.45kg/m ³
Yield strain	5.50%
Compressive strength	66 MPa
Ultimate tensile strength	52 MPa
Ring bending modulus (3mins)	3200 MPa
Ring bending modulus (50 years)	1400 MPa
Poissons ratio	0.38

Thermal

Coefficient of thermal expansion	7x10 ⁻⁵ /°C
Thermal conductivity	0.138-0.150 W.m-1.K-1
Maximum practicable working temperature	60°C

PVC-U DWV

D00222588

DN225 X 45D DWV PVC-U Bend FF SWJ

Fire resistance

Flammability	Self extinguishing. Will not support combustion.
Ignitability - AS 1530*	7*
Smoke Development - AS 1530*	9*
Spread of flame - AS 1530*	0*
Heat evolved - AS 1530*	2*

*AWTA test report number 7- 558788-CV

Electrical

Volume resistivity	10^{15} ohm.cm
Surface resistivity	$\geq 10^{13}$ ohm

Standards

Product standard	AS/NZS 1260 PVC Pipes and Fittings for Drain, Waste and Vent Applications.
Environmental accreditation	Best Environmental Practice PVC - BEP PVC Certification No. BEP-PVC 0037
Product appraisals	WaterMark Certification: WMKA1305 WSSA PA 1625

© Iplex Pipelines Australia Pty Limited 2025. All drawings and information contained within this document are the exclusive property of Iplex. Iplex reserves the right to change product specifications and other information without prior notification. Measurements provided are for reference purposes only. Information in this publication is given in good faith and no warranty is provided or is to be implied with respect to either the information or the product, in particular the suitability of the product for any particular purpose. The purchaser should independently determine the suitability of the product for the intended application.