

PE Systems

EHCX17225M

PE100 Polyethylene Pipe Metric DN225 SDR17 x 12 m
 Co-Ex Orange Electrical

Application

Used to protect electrical cables

Features

- Lightweight
- Durable
- Long Service Life
- Environmentally Friendly
- Corrosion and Chemical Resistance

Technical Data

Product Properties

Material	Polyethylene
Colour	Orange coating
Approximate mass	108.86 kg
Unprotected UV exposure	2 years in accordance with AS/NZS 2033 yr
End connection	Spigot / Spigot
Rating	SDR17

*For short term, intermittent exposure. Contact Iplex for further details

Product Dimensions

Minimum effective length	12000 mm
Nominal size	225 mm
Mean pipe OD	225.0 mm
Mean pipe ID	179.6 mm

Packaging Information

Crate quantity	11
----------------	----

Jointing Details

Joint type	Electrofusion, butt weld, mechanical
Minimum radius of pipe curvature	25 (x DN) Ref: PIPA POP202

PE Systems

EHCX17225M

Standards

Environmental Declarations and Standards

Product standard

Manufactured to the dimensions of AS/NZS 4130

Material Properties

Mechanical

Density 'specific gravity'	0.95
Tensile yield strain (50 mm/min)	8 - 10%
Tensile modulus	900 MPa
Yield stress	25 MPa
Hardness shore D	63
Poissons ratio	0.4
Ring bending modulus (3 mins)	950 MPa
Apparent ring bending modulus (50 years)	260 MPa
Ultimate tensile strength	23 MPa
Compressive strength	32 MPa
Design stress	8 MPa
Maximum support spacing of pipe graded	2.50 m
Maximum support spacing of pipe vertical	5.00 m (Reference AS/NZS 2033, applicable to above ground installations)

Thermal

Coefficient of thermal expansion	$1.8 \times 10^{-4}/^{\circ}\text{C}$
Thermal conductivity	$0.38 \text{ W}\cdot\text{m}^{-1}\cdot\text{K}^{-1}$
Specific heat	$1.9 \text{ J}\cdot\text{kg}^{-1}\cdot\text{K}^{-1}$
Vicat softening temperature	116°C
Allowable operating temperature - degrees	Refer Page 7_Table 2.2 of the Iplex Polyethylene Technical Guide (v 1.2)

PE Systems

EHCX17225M

Fire Resistance

Flammability	Supports combustion, will burn when sufficient heat and oxygen are provided
Ignitability - AS 1530*	13
Smoke development - AS 1530*	3
Spread of flame - AS 1530*	7
Heat evolved - AS 1530*	6

*AWTA test report number 7-558788-CV

Need help? | Merchants 1300 0 47539 | Civil 13 10 86

www.iplex.com.au