

PE Systems

EHCX11140100

PE100 Polyethylene Pipe Metric DN140 SDR11 x 100 m Co-Ex Orange Electrical

Application

Used to protect electrical cables

Features

- Lightweight
- Durable
- Long Service Life
- Environmentally Friendly
- Corrosion and Chemical Resistance

Technical Data

Product Properties

Material	Polyethylene
Colour	Orange coating
Approximate mass	515.868 kg
Unprotected UV exposure	2 years in accordance with AS/NZS 2033 yr
End connection	Spigot / Spigot
Rating	SDR11

*For short term, intermittent exposure. Contact Iplex for further details

Product Dimensions

Minimum effective length	100000 mm
Nominal size	140 mm
Mean pipe OD	140.0 mm
Mean pipe ID	111.8 mm

Jointing Details

Joint type	Electrofusion, butt weld, mechanical
Minimum radius of pipe curvature	15 (x DN) Ref: PIPA POP202

Standards

Environmental Declarations and Standards

Product standard	Manufactured to the dimensions of AS/NZS 4130
------------------	---

Material Properties

Mechanical

Density 'specific gravity'	0.95
Tensile yield strain (50 mm/min)	8 - 10%
Tensile modulus	900 MPa
Yield stress	25 MPa
Hardness shore D	63
Poissons ratio	0.4
Ring bending modulus (3 mins)	950 MPa
Apparent ring bending modulus (50 years)	260 MPa
Ultimate tensile strength	23 MPa
Compressive strength	32 MPa
Design stress	8 MPa
Maximum support spacing of pipe graded	1.70m
Maximum support spacing of pipe vertical	3.40 m (Reference AS/NZS 2033, applicable to above ground installations)

Thermal

Coefficient of thermal expansion	$1.8 \times 10^{-4}/^{\circ}\text{C}$
Thermal conductivity	$0.38 \text{ W}\cdot\text{m}^{-1}\cdot\text{K}^{-1}$
Specific heat	$1.9 \text{ J}\cdot\text{kg}^{-1}\cdot\text{K}^{-1}$
Vicat softening temperature	116°C

Fire Resistance

Flammability	Supports combustion, will burn when sufficient heat and oxygen are provided
Ignitability - AS 1530*	13
Smoke development - AS 1530*	3
Spread of flame - AS 1530*	7
Heat evolved - AS 1530*	6

*AWTA test report number 7-558788-CV

Need help? | Merchants 1300 0 47539 | Civil 13 10 86

www.iple.com.au